



Product Information

Project		Part	IBPM.756170.074
Dimension	49.1x100.1x16.1	Weight	16.8g
Material	PC 2180T	Shrinkage	1.005
Even Thickness	1.5mm	Marks	-
Finishing	SPI A2	Color	SPI A2

Mold Information


Supplier	TTM	Mold No.	TTM-2340
Mold Type	2 plate mold	Runner Type	Side Gate
Cavity	1*2	Mold Standard	Mold base LKM components is imitated HASCO
Location Ring	Ø125	Sprue Radius	SR15.5
Nozzle Type	HASCO Z80HT	Mold Life	500000 shots
Slider	-	Lifter	-
Cavity	S136 HRC48-52	Core	S136 HRC48-52
Slider material	-	Lifter Material	-

1. Please confirm above detail information.

Svetotehnika: OK



Mold Layout / Structure



Item		Injection machine Tonnage	Mold information
Will you offer the injection machine tonnage?	Yes	ENGEL 500/90	
Clearance between Tie Bars			280*400
Shot Weight/ Part weight		N/A	33.6 g
Mold thickness		N/A	
Location ring		125	124.8
Nozzle R		N/A	SR20

Customer comment. (please give your approval and comments)


OK or NG	Remark	Approval by:	Date

Svetotehnika: OK

2.Please confirm the mold structure.



Product Image






Customer comment. (please give your approval and comments)

OK or NG	Remark	Approval by:	Date

3.Part size: 49.1x100.1x16.1



Parting Line



Customer comment. (please give your approval and comments)



OK or NG	Remark	Approval by:	Date

4. Pls confirm the parting line.

Svetotehnika: OK



Injection Gate





5. injection gate is side gate, pls check.

Svetotehnika: OK

Customer comment. (please give your approval and comments)			
OK or NG	Remark	Approval by:	Date



Ejector Type




- — Ø3 Ejector Pin (4PCS)
- — Ø4 Ejector Pin (12PCS)

6. pls confirm the ejector pin size and location.

Customer comment. (please give your approval and comments)			
OK or NG	Remark	Approval by:	Date



Draft Analysis





Finishing	Draft angle for reference
Non-appearance surface	>0.5°-1°
High gloss	1.5°-2°
Finest texture	1.5°-2°
Fine texture	2°-3°
Rough texture	2.5 °-3.5°

7. draft angle meets the requirement.



Thickness Analysis




8. red area is too thick will cause sink mark, suggest to reduce the material, but as the design limitations, we don't have idea to reduce, so will try to improve it by injection parameters, but we cannot ensure it won't have sink mark totally, pls note.

Customer comment. (please give your approval and comments)			
OK or NG	Remark	Approval by:	Date



Part surface finish



green area SPI A-2

Customer comment. (please give your approval and comments)


OK or NG	Remark	Approval by:	Date

9. pls confirm the surface finish.



Surface defect E
(sink mark)
缩水痕

Problem E: When the thickness is not even, the rib thickness exceeds 60% of the main thickness, it will have sink mark problem. Different proportion will have different sink mark.

Solution: Make the thickness even, the rib thickness can not exceed 60% of the main thickness



$$B(\text{rib thickness}) = 60\% \times A(\text{main thickness})$$



As the above show, there is sink mark as the picture of product we made. For reference



Thank you very much

